

Chemical Resistance Data

Chemical Name	SprayGuard® ¹	Tychem® SL* and Tychem 4000
	Mfg:Indutex	Mfg:Dupont
ACETIC ACID	>480	>480
ACETONE	>480	immed.
Acetonitrile		68
AMMONIUM HYDROXIDE	>480	
Ammonia		32
1,3-Butadine		>480
CARBON DISULFIDE		immed.
Chlorine		>480
DICHLOROMETHANE		immed.
DIETHYLAMINE		12
N,N-Dimethylformamide		78
ETHYL ACETATE		immed.
Ethylene Oxide		immed.
FORMIC ACID	>480	
Glycerol	74	
n-Hexane		immed.
Hydrogen Chloride		>480
HYDROCHLORIC ACID	>480	
HYDROGEN PEROXIDE, 70%	400	
Isophorone Diamine	>480	
Methanol		>480
Methyl Chloride		>480
MERCURIC CHLORIDE	>480	
METHYL ISOCYANATE		
NITRIC ACID, 30%	>480	
Nitrobenzene		102
Phosphoric acid	>480	
POTASSIUM CHROMATE	>480	
Potassium cyanide (sat'd)	>480	
POTASSIUM HYDROXIDE, 45%	>480	
SODIUM HYDROXIDE, 42-50%	>480	>480
SULFURIC ACID	>480	>480
Sodium acetate (sat'd)	>480	
Sodium fluoride (sat'd)	>480	
Sodium Hypochlorite	>480	
SULFURIC ACID	>480	
1,1,2,2-TETRACHLOROETHYLENE	>480	immed.
TETRAHYDROFURAN		immed.
Sodium chloride	>480	
Vinorelbine	>480	
Thio TEPA	>480	
Paclitaxel	>480	
Oxaliplatin	>480	
Mitomycin	>480	
Irinotecan	>480	
Ganciclovir	>480	
5-Fluorouracil	>480	
Doxorubicine HCl	>480	
Cisplatin	>480	
Carmustine	>480	
Butan-1-ol	>480	
Toluene	>480	immed.

immed. = Immediate Breakthrough

¹ = Puntiform® material is used to make the SprayGuard® Garments

* Lab results published on www.DuPont.com

Tychem® SL is a registered trademark of E.I. duPont de Nemours and Compar

SprayGuard® is a registered trademarks of Indutex S.p.A.