

Chemical Resistance Data

March 2008

			Breakthrough time (Normalized - in min.)
CAS Number	Chemical Name / Synonym	Concentration [%]	Class 3 Ensemble ¹ JetGuardPLUS ¹ Mfg:Indutex
127-18-4	1,1,2,2-TETRACHLOROETHYLENE	95+	>480
120-82-1	1,2,4- Trichlorobenzene	95+	60
79-95-8	2,2',6,6'- Tetrachlorobiphenol	95+	>480
107-07-3	2-CHLOROETHANOL	95+	>480
75-07-0	ACETALDEHYDE	95+	>480
64-19-7	ACETIC ACID	95+	>480
67-64-1	ACETONE	95+	244
75-05-8	ACETONITRILE	95+	>480
107-02-8	ACROLEIN	95+	>480
79-06-1	ACRYLAMIDE	50% in water	>480
107-13-1	ACRYLONITRILE	95+	>480
107-18-6	ALLYL ALCOHOL	95+	>480
107-05-1	ALLYL CHLORIDE	95+	>480
7664-41-7	AMMONIA GAS	95+	>480
1336-21-6	AMMONIUM HYDROXIDE	28-30	>480
628-63-7	Amyl acetate n-	95+	>480
62-53-3	ANILINE	95+	>480
120-12-7	Anthracene (sat'd. in toluene)	95+	>480
7647-18-9	Antimony pentachloride	95+	>480
71-43-2	Benzene	95+	>480
100-47-0	BENZONITRILE	95+	455
7726-95-6	BROMINE	95+	56
142-96-1	BUTYL ETHER N-	95+	>480
75-15-0	CARBON DISULFIDE	95+	77
56-23-5	CARBON TETRACHLORIDE	95+	>480
7782-50-5	CHLORINE GAS	95+	>480
79-11-8	CHLOROACETIC ACID	95+	>480
108-90-7	CHLOROBENZENE	95+	4
107-07-3	Chloroethanol 2-	95+	>480
67-66-3	CHLOROFORM	95+	>480
107-30-2	CHLOROMETHYL METHYL ETHER	95+	>480
8001-58-9	Creosote	95+	>480
95-48-7	Cresol-o	95+	>480
110-82-7	CYCLOHEXANE	95+	>480
117-81-7	DI (2-ETHYLHEXYL) PHTHALATE	95+	>480
75-09-2	DICHLOROMETHANE	95+	105
70892-10-3	Diesel fuel	95+	>480
109-89-7	DIETHYLAMINE	95+	>480
127-19-5	DIMETHYL ACETAMIDE N, N-	95+	>480
62-75-9	Dimethyl nitrosamine	95+	>480
75-18-3	Dimethyl sulphide	95+	>480
68-12-2	DIMETHYLFORMAMIDE N,N-	95+	>480
123-91-1	Dioxane 1,4-	95+	>480
106-89-8	EPICHLOROHYDRIN	95+	>480
141-43-5	ETHANOLAMINE	95+	>480
141-78-6	ETHYL ACETATE	95+	>480
111-15-9	ETHYL CELLOSOLVE(R) ACETATE	95+	>480
107-15-3	ETHYLENE DIAMINE	99	>480
106-93-4	ETHYLENE DIBROMIDE	95+	>480
107-21-1	Ethylene Glycol	95+	>480
462-06-6	FLUOROBENZENE	95+	>480
50-00-0	FORMALDEHYDE GAS	37	>480
64-18-6	FORMIC ACID	95+	>480
98-01-1	FURFURAL	95+	137
86290-81-5	GASOLINE, LEADED	95+	>480

Chemical Resistance Data

March 2008

			Breakthrough time (Normalized - in min.)
CAS Number	Chemical Name / Synonym	Concentration [%]	Class 3 Ensemble ¹ JetGuardPLUS ¹ Mfg:Indutex
822-06-0	Hexamethylene diisocyanate	95+	>480
110-54-3	HEXANE, N-	95+	>480
302-01-2	HYDRAZINE	95+	>480
7647-01-0	HYDROCHLORIC ACID	37	>480
7664-39-3	HYDROFLUORIC ACID	70	>480
7664-39-3	HYDROFLUORIC ACID	50	>480
7803-57-8	Idrazine Monohydrate	95+	>480
99-63-8	Isophthaloyldichloride	95+	>480
67-63-0	ISOPROPYL ALCOHOL	95+	>480
8008-20-8	Kerosene (Jet A fuel)	95+	>480
541-25-3	LEWISITE (L) CHEMICAL AGENT	95+	>1440
7487-94-7	MERCURIC CHLORIDE	sat.	>480
67-56-1	METHANOL	95+	361
78-93-3	METHYL ETHYL KETONE	95+	>480
108-10-1	METHYL ISOBUTYL KETONE	95+	11
624-83-9	METHYL ISOCYANATE	95+	9
78-94-4	Methyl vinyl ketone	95+	>480
108-10-1	Methyl-2-pentanone 4-	95+	11
74-95-3	Methylene bromide	95+	312
75-09-2	Methylene chloride	95+	>480
1634-04-4	Methyl-t-butyl-ether	95+	>480
505-60-2	MUSTARD (HD) CHEMICAL AGENT	95+	>1440
91-20-3	Naphthalene	95+	>480
7697-37-2	NITRIC ACID, 70%	70	>480
7697-37-2	NITRIC ACID, 90%	90	>480
98-95-3	NITROBENZENE	95+	>480
10102-44-0	Nitrogen dioxide	95+	>480
8006-61-9	Petrol, unleaded	95+	>480
108-95-2	PHENOL	85+	>480
7664-38-2	PHOSPHORIC ACID	85	>480
10025-87-3	PHOSPHOROUS OXYCHLORIDE	95+	>480
7719-12-2	Phosphorous Trichloride	95+	>480
11097-69-1	Polychlorinated biphenyl (PC)	95+	>480
7789-00-6	POTASSIUM CHROMATE	sat. in water	>480
75-56-9	PROPYLENE OXIDE 1,2-	95+	>480
107-44-8	SARIN (GB) CHEMICAL AGENT	95+	>1440
143-33-9	SODIUM CYANIDE	95+	>480
1310-73-2	SODIUM HYDROXIDE, 42-50%	50	>480
7681-52-9	Sodium hypochlorite (30% ch)	95+	>480
96-64-0	SOMAN (GD) CHEMICAL AGENT	95+	>1440
96-09-3	Styrene Oxide	95+	>480
7446-09-5	SULFUR DIOXIDE	95+	>480
7446-09-5	Sulphur dioxide	95+	>480
77-81-6	TABUN (GA) CHEMICAL AGENT	95+	>1440
109-99-9	TETRAHYDROFURAN	95+	>480
1118-46-3	Tin chloride, Mono-n-butyl	95+	>480
1464-22-9	Tin chloride, Tri-n-butyl	95+	>480
584-84-9	TOLUENE-2,4-DIISOCYANATE	95+	>480
95-53-4	TOLUIDINE O-	95+	>480
76-03-9	Trichloroacetic acid	95+	>480
120-82-1	TRICHLOROBENZENE 1,2,4-	95+	60
76-05-1	Trifluoroacetic acid	95+	>480
935-92-2	Trimethyl chinon	95+	>480
108-05-4	VINYL ACETATE	95+	>480

imm. = Immediate Breakthrough

1 = Tessaform® materials is used to make the JetGuardPLUS®, Class 3 Ensemble®, and GasGuardT2 Puntiform®, Tessaform®, Duoform® are registered trademarks of Indutex S.p.A.